Plagiarism Checker X - Report

Originality Assessment

0%

Overall Similarity

Date: Feb 23, 2026 (01:00 PM)
Matches: 0 / 2591 words
Sources: 0

Remarks: No similarity found, your document looks healthy.

Verify Report:
Scan this QR Code

Electrical and Morphological Characterization of Solution-Processed Gel/PZN-PT Perovskite Nanoparticles Thin Film for Transistor Dielectrics.

Abstract:

Thin film filed effect transistors (TFTs) have drawn significant attention from scientific community as one of the most attractive for low-cost, large area and flexible electronics.In this context, the development of high-k dielectric materials with additional functional properties is essential for low voltage operating and enhancement of device performance. This work presents the investigation of solution processed Pb(Zn1/3Nb2/3)O3-4.5PbTiO3(PZN-PT) perovskite nanoparticles thin films, with and without Mn doping, as gate dielectrics for thin film transistor applications. PZN-PT with 1% Mn doped and undoped PZN-PT films were deposited by spin coating on nanostructured doped n-type silicon substrate to form metal-oxide-semiconductor (MOS) structures with top silver contact. SEM analysis shows Mn doping PZN-PT presents a denser and more homogeneous microstructure compared to undoped. Electrical measurements confirmed transistor operating mode and highlighted the effect of ferroelectric polarization on device behavior. The results show that device from PZN-PT Mn doped films exhibit higher values of current □2.5x10-1 A and more electrical stability than the undoped device.

Keys word:

PZN-PT nanoparticles, Perovskites, Ferroelectric, Dielectric, Thin Film Transistor.

1. Introduction

Flexible and thin film electronics has emerged as a promising technology for low-cost, large area microelectronic applications RFID tags and smart labels. Organic–inorganic perovskite materials are currently attracting considerable attention as an absorber for highly efficient solar cells[1,2].For several decades, silicon oxide SiO2 has been used as the gate dielectric material in Si-based MOSFETs and organic field effect transistors OFETs due to the high quality of the Si/SiO2 interface and its mature processing technology. However, the low dielectric constant value of SiO2[3] limits further voltage

scaling. As a result, several materials like HfO2[4] and Al2O3[5] and biopolymer Gum [6–9] have been investigated as dielectric material to enhance gate insulator capacitance and reduce leakage currents. Recent researches have focused attention on using perovskite materials in field-effect transistors because perovskites promise the processability and flexibility inherent to thin film transistors as both dielectric and semiconductor materials [10–14]. Perovskite oxides with high dielectric constants offer a unique opportunity to serve as gate dielectric and to introduce ferroelectric functionality. The ferroelectric functionality opens pathways toward ferroelectric field effect transistors (FeFETs) and non-volatile memory devices[15–17].When placed in the context with conventional SiO2 dielectric[18], Pb(Zn1/3Nb2/3)O3-4.5PbTiO3(PZN-PT)and 1% Mn-doped PZN-PT materials offer a distinct advantage due to its high dielectric constant in bulk [19,20] and inthin film [21]. AmongPZN-PT solution processed thin films represent a promising pathway toward future thin film electronic devices. However, the performance of solution processed thin films materials depends highly on film microstructure, nanoparticle dispersion and defect density. Structural defects, grain boundaries and poor film densification can lead to increase leakage currents and charge trapping. Therefore, an investigation of the effect between film morphology and electrical behavior is necessary to optimize PZN-PT thin film based dielectric in transistors architectures.

In this work, we investigate the applicability of solution processedPb(Zn1/3Nb2/3)O3-4.5PbTiO3(PZN-PT) PZN-PT nanoparticle thin films, with and without Mn doping, as gate dielectrics for transistors in top gate configuration.

2. Experimental Procedure

Pb(Zn1/3Nb2/3)O3-4.5PbTiO3(PZN-PT) nanoparticles thin film wasgrown on nanostructured silicon doped ntype as substrate to form a p-MOS channel structure. PZN-PT perovskite material is previously grinded and dispersed in a gel to obtained homogeneous solution. Substrates are firstly cleaned with acetone and alcohol with ultrasonic baht. PZN-PT nanoparticles thin film is deposited by spin coating as dielectric material on the nanostructured silicon.To ensure ferroelectric properties effect on electrical

behaviour of the transistors, we processed two different devices in top contact structure. Device 1 was made from non-doped PZN-PT nanoparticles thin film. In contrast, device 2 was made with 1% Mn doped PZN-PT film.The Gate, Source and Drain contact were fabricated bylayering silver over several millimeters to form a top contacts structure of film effect transistor as illustratedin Fig. 1. SEM analysis were performed by using a MERLIN FEG of Zeiss scanning electronmicroscopy (SEM) model to carried out the surface morphology of the film but also to observe the dispersion of the nanoparticles in the deposited film. Electrical characterization was performed with a KEITHLEY 2612B source-meter to observe output and transfer characteristics drain current. As we couldn't estimate the capacitance of the dielectric, we didn't evaluate the field effect mobility of free charges carries of the active material.

Fig. 1: Schematic structure PZN-PT nanoparticles thin film as gate dielectric

3. Results and Discussion

The morphological and electrical characterization of the PZN-PT thin films provides critical insights into the role of Mn doping and the intrinsic ferroelectric nature of PZN-PT material when applied as a high-k dielectric.

3.1 SEM Morphological Analysis

SEM analysis clearly distinguished the differences between the undoped and Mn-doped thin films.The Mn-doped PZN-PT films (image a) exhibited a compact microstructure with uniformly distributed grains, which implies a stable crystallization pathway.The Mn-doped films exhibited denser structures and uniform nanoparticle distribution, with average grain sizes lower than those undoped ones.On the other hand,the undoped films in imageb shows grain agglomeration and rough surfaces, with visible pores and cracks.The observed structural differences are attributed to the acceleratedcrystallization kinetics induced by Mn doping, which acts as a sintering aid. Accelerated the kinetics process of PZT thin film leads to better crystallization and avoids or minimises the interfacial defect [22]. Meanwhile the grain growth observed in undoped film introduces structural defects

that could compromise dielectric reliability. Ndioukaneet al. found colossal relative dielectrics constant at 1kHz of PZN-PT and its 1% Mn doped thin film respectively about 2.76□104 and 17.7□104[21].This difference values also shows the effect of Mn doping in the structure ofthe formed thin film on silicon substrate. Daus et al. shows in their study on methyl-ammonium lead iodide (MAPbI3) a giant value of dielectric constant □1000 as gate dielectric material for thin film transistors [23]. These different studies should encourage the use of perovskite materials as high k dielectric material in field effect transistors.

Fig. 2: SEM images of PZN-PTthin film: a) 1% Mn doped; b) Undoped

3.2 Electrical Measurements

The electrical output characteristics shown in Fig.3a&b presents difference in drain current magnitude. Both Mn-doped and undoped electrical characteristics demonstrated transistor-like behavior. And shows that the devices operate in p-type transistor. Which could confirm the feasibility of integrating PZN-PT perovskite material into thin film field effect transistor architectures.The Mn-doped films displayed more stable and higher drain current responsesFig.3a. The highest drain current obtained in p-type channel transistor is over -250 mA at Vg = -10 V. SEM image of Mn-doped with better crystallization and dense structure could explain the high values of drain current and lower presence of leakage current. Ndioukane et al. showed enhanced open circuit voltage on Mn-doped PZN-PT perovskite thin film solar cell over undoped, where they explained it to the lattice-free crystallization induced by the Mn doping [24]. Mn2+ ions replaced B-site cations in the perovskite lattice. This replacement leads to improve lattice symmetry and defects passivation. Therefore, the Mn doping reduced trap states and enhanced the interfacial quality. One could also suggest that the Mn-doping enhanced polarization of PZN-PT thin film and reduced the leakage current which made the dielectric more effective for low voltage operation.

In contrast, the undoped devices present lower drain current less than -100 mA at the same gate voltage Fig.3b. As it is shown previously in SEM image, the dependence of

electrical performance and film structure is clearly observed. The undoped devices suffered leakage current observed in Fig.3b. The structural defects observed in undoped films could compromise the positive impactof dielectric proprieties and increase the observed leakage current. The lower values of drain current and instability of electrical parameters of undoped devices are similar of previous results in electrical dependencywith the dielectric interface quality in field effect transistors[18,25–27]. The poor quality of the dielectric interface due toundoped film defects could induce charge trapping and carrier scattering. Moreover, the gate and dielectric contact resistance should be high because of the poor quality of the undoped film microstructure. And then, the injection and/or charges collection would be lower. Since this perovskite material should be proposed as gate dielectric, better interface quality is necessary to improve and stabilize the electrical characteristics of devices. However, Ndioukane et al. presented Mn doping as stabilizer of the electric field dependence of PZN-PT film[21].Moreover, the absence of dielectric capacitance measurements limited quantitatively the benchmarking of this study. The FETs keys parameters such like field effect mobility was not calculated.

Fig. 3: Output electrical characteristics of PZN-PT as dielectric transistor:a) 1% Mn doped b) non-doped.

3.3 Ferroelectric effect in devices operating

A particularly observation in Fig.4a&b is the manifestation of ferroelectric polarization in the PZN-PT dielectric at the values of Vg=± 20 V. The polarization leads to hysteresis in the output curves.This behavior indicates the dual role of the material as both high-k and ferroelectric proprieties. This ferroelectric behavior is in strong agreement with the growing studies in ferroelectric field effect transistors (FeFETs), where polarization switching enhances non-volatile behavior [17,28]. The coercive field Ec(Fig4.b) is about 20 V/cm proportionally to our devices dimensions for the undoped and Mn-doped one. The doping has no effect on the coercive field as the ferroelectricity propriety is typically based on the PZN-PT perovskite material. This value is in accordance with the coercive field values

given by Ndioukane et al.[21].

Fig. 4: Ferroelectric effect over transistor Output characteristics a) from variable voltage of Vg and b) Vg fixed at -20 and 20.

4. Conclusion

This work demonstrates the successful fabrication and characterization of PZN-PT thin film as dielectric for transistors applications. Mn-doped films exhibit compact and dense microstructure and morphology. Devices from the doping PZN-PT material present superior electrical stability with drain current over 250 mA. Whereas the undoped PZN-PT films, even developing grain growth, present defects that decrease device performance. The ferroelectric nature of the PZN-PT perovskite material is showed in hysteresis effect, which confirming its potential application in ferroelectric field effect transistors (FeFETs).

Acknowledgements

References

[1] Ndioukane R, Kobor D, Motte L and Solard J 2019 Optical properties of PZN-PT nanoparticles thin layer on ITO glass for photovoltaic application OAJ Mater. Devices4

[2] Ndioukane R, Touré M, Diallo A K, Fall N C Y, Kobor D, Motte L, Ottaviani L and Torchio P PHOTOVOLTAIC PROPERTIES OF PZN-4.5PT PEROVSKITE NANOPARTICLES THIN FILM DEPOSITED ON SILICON NANOWIRES SUBSTRATE 3

[3] Gutowski M, Jaffe J E, Liu C-L, Stoker M, Hegde R I, Rai R S and Tobin P J 2002 Thermodynamic stability of high-K dielectric metal oxides ZrO2 and HfO2 in contact with Si and SiO2 Appl. Phys. Lett.80 1897–9

[4] Kang T, Park J, Jung H, Choi H, Lee S-M, Lee N, Lee R-G, Kim G, Kim S-H, Kim H, Yang C-W, Jeon J, Kim Y-H and Lee S 2024 High-κ Dielectric (HfO2)/2D Semiconductor (HfSe2) Gate Stack for Low-Power Steep-Switching Computing Devices Adv. Mater.36 2312747

[5] Bencherif H, Yousfi A, Dehimi L, Pezzimenti F and Corte F G D 2019 Analysis of Al2O3

high-k gate dielectric effect on the electrical characteristics of a 4H-SiC low-power MOSFET 2019 1st International Conference on Sustainable Renewable Energy Systems and Applications (ICSRESA) 2019 1st International Conference on Sustainable Renewable Energy Systems and Applications (ICSRESA) pp 1–4

[6] Tall A, Diallo A K, Erouel M, Seck M, Chouiref L, Saadi M, Wederni M A, Ly E H B, Diallo A, Bouguila N, Kobor D and Khirouni K 2022 Electrical and Dielectrical Properties of Khaya Gum Biopolymer Thin Filmcoated by Spray Pyrolysis Technique J. Sol-Gel Sci. Technol.104 401–11

[7] Erouel M, Saadi M, Tall A, Tiss B, Seck M, Diallo A K, Ly E H B, Kobor D, Bouguila N and Khirouni K 2023 Structural and electrical properties of cashew gum thin film deposited by spray pyrolysis Polym. Renew. Resour.14 76–93

[8] Seck M, Mohammadian N, Diallo A K, Faraji S, Saadi M, Erouel M, Ly E H B, Khirouni K and Majewski L A 2020 Low voltage organic transistors with water-processed gum arabic dielectric Synth. Met.267 116447

[9] Tall A, Faraji S, Diallo A K, Mohammadian N, Erouel M, Seck M, Saadi M, Khirouni K and Majewski L A 2022 Khaya gum – a natural and eco-friendly biopolymer dielectric for low-cost organic field-effect transistors (OFETs) J. Mater. Sci. Mater. Electron.33 15283–95

[10] Canicoba N D, Zagni N, Liu F, McCuistian G, Fernando K, Bellezza H, Traoré B, Rogel R, Tsai H, Le Brizoual L, Nie W, Crochet J J, Tretiak S, Katan C, Even J, Kanatzidis M G, Alphenaar B W, Blancon J-C, Alam M A and Mohite A D 2019 Halide Perovskite High-k Field Effect Transistors with Dynamically Reconfigurable Ambipolarity ACS Mater. Lett.1 633–40

[11] Hoffmann M, Slesazeck S and Mikolajick T 2021 Progress and future prospects of negative capacitance electronics: A materials perspective APL Mater.9 020902

[12] Jana S, Carlos E, Panigrahi S, Martins R and Fortunato E 2020 Toward Stable Solution-Processed High-Mobility p-Type Thin Film Transistors Based on Halide Perovskites ACS Nano14 14790–7

[13] Kim J Y, Choi M-J and Jang H W 2021 Ferroelectric field effect transistors: Progress and perspective APL Mater.9 021102
[14] Wu T, Pisula W, Rashid M Y A and Gao P 2019 Application of Perovskite-Structured Materials in Field-Effect Transistors Adv. Electron. Mater.5 1900444
[15] Mulaosmanovic H, Chicca E, Bertele M, Mikolajick T and Slesazeck S 2018 Mimicking biological neurons with a nanoscale ferroelectric transistor Nanoscale10 21755–63
[16] Singh P, Jha R K, Singh R K and Singh B R 2018 Electrical properties of Pb[Zr0.35Ti0.65]O3 on PEALD Al2O3 for NVM applications Microelectron. Int.35 189–96
[17] Kim J Y, Choi M-J and Jang H W 2021 Ferroelectric field effect transistors: Progress and perspective APL Mater.9 021102
[18] Gruber D 2024 The use of high-k dielectrics in MOSFETs Medium
[19] Kobor D, Albareda A, Perez R, Garcia J, Lebrun L and Guyomar D 2005 Dielectric and mechanical nonlinearities of lang001rang oriented pure and doped single crystals of PZN-4.5PT J. Phys. Appl. Phys.38 2258–64
[20] Kobor D, Tine M, Hajjaji A, Lebrun L and Guyomar D 2012 Mn Effect on Nonlinear and Structural Properties of Oriented PZN-4.5PT Single Crystals J. Mod. Phys.3 404–11
[21] Ndioukane R, Touré M, Kobor D, Motte L, Solard J and Lebrun L 2019 Dielectric and Ferroelectric Properties of PZN-4.5PT Nanoparticles Thin Films on Nanostructured Silicon Substrate for Ferrophotovoltaic and Energy Storage Application J. Mod. Phys.10 613–23
[22] Araújo E B and Eiras J A 2003 Effects of crystallization conditions on dielectric and ferroelectric properties of PZT thin films J. Phys. Appl. Phys.36 2010
[23] Daus A, Roldán-Carmona C, Domanski K, Knobelspies S, Cantarella G, Vogt C, Grätzel M, Nazeeruddin M K and Tröster G 2018 Metal-Halide Perovskites for Gate Dielectrics in Field-Effect Transistors and Photodetectors Enabled by PMMA Lift-Off Process Adv. Mater.30 1707412
[24] Ndioukane R, Touré M, Diallo A K, Fall N C Y, Kobor D, Motte L, Ottaviani L and Torchio P PHOTOVOLTAIC PROPERTIES OF PZN-4.5PT PEROVSKITE NANOPARTICLES THIN FILM DEPOSITED ON SILICON NANOWIRES SUBSTRATE 3

[25] Pyo S, Lee Y, Jeon J, Yi M H and Kwon S-K 2006 Effect of a gate insulator with a long alkyl side chain on the performance of pentacene organic thin-film transistors J. Appl. Phys.99 073711

[26] Jung Y, Kline R J, Lin E K, Fischer D A, Toney M F, Heeney M, McCulloch I and DeLongchamp D 2008 The Impact of the Dielectric/Semiconductor Interface on Microstructure and Charge Carrier Transport in High-Performance Polythiophene Transistors ECS Trans.13 113–22

[27] Sun X, Di C and Liu Y 2010 Engineering of the dielectric–semiconductor interface in organic field-effect transistors J. Mater. Chem.20 2599

[28] Mai M, Ke S, Lin P and Zeng X 2015 Ferroelectric Polymer Thin Films for Organic Electronics J. Nanomater.2015 812538

EXCLUDE CUSTOM MATCHES	ON
EXCLUDE QUOTES	OFF
EXCLUDE BIBLIOGRAPHY	OFF