



Plagiarism Checker X - Report

Originality Assessment

0%

Overall Similarity

Date: Jun 9, 2026 (02:39 PM)

Matches: 0 / 8891 words

Sources: 0

Remarks: No similarity found,
your document looks healthy.

Verify Report:

Scan this QR Code



Synthesis and characterization of zeolitic catalysts by the Plackett and Burman (PB) plan method using local materials from Niger.

ABSTRACT

Zeolite catalysts have become the most widely used materials in the crude oil refining industry. Zeolite catalysts were synthesized using clays (raw D1 and treated D2) and sand (SM) sampled in Niger (Maradi). Characterization tests were performed on D1, D2, and SM using conventional techniques (CEC, PAF, XRD, FRX, FTIR, BET, and SEM). These techniques revealed the presence of 96% non-swelling clays and 4% swelling clays. The silica-alumina ratio (SAR) of the sand is 43.28. Based on these compositions, various chemical mixtures (D1, D2, SM, aluminum isopropoxide $\text{Al}(\text{OCH}(\text{CH}_3)_2)_3$ or $\text{Al}(\text{O-i-Pr})_3$, sodium hydroxide NaOH, and distilled water) were prepared to synthesize the catalysts following the factor screening plan according to the Hadamard matrix. After synthesis, the experimental results showed that the influential factors are aluminum isopropoxide, clay, stirring time, drying time, and calcination temperature. Using the Boehm test, the screening plan made it possible to record a response characterizing the catalytic activity, namely the acidity (Y_{exp}) on the surface of the catalysts. The results indicated that Y_{exp} of the catalysts varies between 15 and 65 meq/g. Three best catalysts, namely CAZ-1, 2, and 7, were selected based on Y_{exp} and then characterized (XRD, FRX, FTIR, BET, SEM, and ATD-ATG). The results of the analyses carried out on the synthesized zeolite catalysts CAZ-1, CAZ-2, and CAZ-7 show that they have mineralogical, chemical, physical, morphological, and thermal characteristics similar to those of zeolite Y and intermediate zeolite Y zeolite catalysts. Of the three selected catalysts, CAZ-2 showed the best results, with a 10.85% increase in light molecules and a catalytic yield of 83%.

Keywords: clay, catalysts, cracking, naphtha, sand.

RESUME :

Les catalyseurs zéolitiques sont devenus les matériaux les plus utilisés dans l'industrie du raffinage de pétrole brut. Des catalyseurs zéolitiques ont été synthétisés en utilisant des

argiles (brute D1 et traitée D2) et du sable (SM) échantillonnés au Niger (Maradi). Des tests de caractérisation ont été réalisés sur D1, D2 et SM en utilisant des techniques classiques (CEC, PAF, DRX, FRX, IRTF, BET et MEB). Ces techniques révèlent la présence de 96% d'argiles non gonflantes et 4% d'argiles gonflantes. La valeur « Silice Alumine Ratio » (SAR) du sable est de 43,28. Au regard de ces compositions, différents mélanges chimiques (D1, D2, SM, isopropoxyde d'aluminium $\text{Al}(\text{OCH}(\text{CH}_3)_2)_3$ ou $\text{Al}(\text{O-i-Pr})_3$, hydroxyde de sodium NaOH et d'eau distillée) ont été préparés en vue de synthétiser les catalyseurs en suivant le plan de criblage des facteurs selon la matrice d'Hadamard. Après la synthèse, les résultats expérimentaux ont montré que les facteurs influents sont l'isopropoxyde d'aluminium, l'argile, le temps d'agitation, le temps de séchage et la température de calcination. En utilisant le test de Boehm, le plan de criblage a permis d'enregistrer une réponse caractérisant l'activité catalytique, c'est l'acidité (Y_{exp}) à la surface des catalyseurs. Les résultats ont indiqué que Y_{exp} des catalyseurs varie entre 15 à 65 méq/g. Trois meilleurs catalyseurs à savoir CAZ-1, 2 et 7 ont été sélectionnés sur la base de Y_{exp} , puis caractérisés (DRX, FRX, IRTF, BET, MEB et l'ATD-ATG). Les résultats des analyses réalisées sur les catalyseurs zéolithiques synthétisés CAZ-1, CAZ-2 et CAZ-7 montrent qu'ils présentent des caractéristiques minéralogique, chimique, physique, morphologique et thermique similaires à celles des catalyseurs zéolithiques de type zéolithe Y et zéolithe Y intermédiaire. Des trois catalyseurs sélectionnés, les CAZ-2 présentent les meilleurs résultats car ils donnent 10, 85% d'augmentation des molécules légères pour un rendement de catalytique de 83%.

Mots clés : argile, catalyseurs, craquage, naphta, sable.

1. Introduction

Over the years, zeolite catalysts with MFI, FAU, BEA, etc. structures have become the most widely used catalytic materials in the crude oil refining industry due to their high acidity and good shape selectivity[1–4]. These catalysts can be synthesized from industrial materials such as Tetrapropylammonium (TPA), industrial silica (LUDOX HS-40), and aluminum isopropoxide (IP). The latter act respectively as a synthesis matrix or support, an

additive providing hardness to the catalysts, and an additive providing the catalysts with reaction sites [5]. Given not only the toxic and polluting nature of the industrial materials (TPA, LUDOX-HS40, IP, etc.) used during catalyst synthesis, but also their high cost, researchers have turned to a much more economical and environmentally friendly alternative using natural, accessible, and less expensive materials such as clay minerals [6]. This led researchers such as Pan. F et al., 2017 [7]; Xing. Y et al., 2017 [8]; Nanzhe et al., 2019 [9]; Yue. Y et al., 2020 [10], and Wu. M et al., 2020 [11] have used kaolinite, attapulgite, illite, rectorite, and palygorskite, respectively, to synthesize zeolite catalysts. These catalysts are generally synthesized using two methods: the dry method, without solvents, in the experimental protocol [12–14], and the hydrothermal method [12–14], and the hydrothermal method [7,9,15]. The hydrothermal method remains the most suitable for synthesizing zeolite catalysts, as the solvent is necessary for proper crystallization of the catalysts [11].

The present work aims to synthesize zeolite catalysts by the hydrothermal process, using clay and sand sampled in Niger. Specifically, clay is used as a synthesis support and sand as a siliceous additive to replace certain industrial siliceous materials such as LUDOX HS-40 used by I. Qoniah et al., 2015 [16] or Florisil used by O. Abdoulaye Dan Makaou et al., 2021 [17] in the synthesis of zeolite catalysts. To date, very little literature has been reported on work aimed at replacing industrial siliceous materials with natural sand in the synthesis of zeolite catalysts using the factor screening method according to the Hadamard matrix. This work aims to contribute further to this field.

After synthesizing zeolite catalysts using the factor screening method, they will be characterized using XRD, XRF, IR, BET, SEM, and ATG-ATD methods. These analytical methods will enable the structure of the synthesized catalysts, their chemical composition, chemical functions, textural properties, morphology, and mass variation as a function of temperature to be studied.

Catalytic cracking tests were conducted on naphtha using the three (3) catalysts to determine their performance.

2. Experimental

2.1. Materials

The clay used as a matrix in the catalyst synthesis procedure is a Nigerian kaolinite clay (D1 : raw clay and D2 : activated clay) which has been the subject of publication in previous work[18]. It comprises 81.8% kaolinite, 14.2% illite and 4% smectite, i.e. 96% non-swelling clays (kaolinite and illite) and 4% swelling clays (smectite). Clay D1 has a BET specific surface area (SS) of 446.50 m²/g, a pore diameter (DP) of 2.12 nm and a micropore volume (VMP) of 0.22 cm³/g, while sample D2 has a BET specific surface area (SS) of 256.3 m²/g, a pore diameter (DP) of 2.10 nm and a micropore volume (VMP) of 0.12 cm³/g. The sand (SM) contains 94.78% SiO₂ and 1.90% Al₂O₃, giving a Silica Alumina Ratio (SAR) of 43.28. In addition to clay and sand, industrial chemicals were also used in the zeolite catalyst synthesis protocol: aluminum isopropoxide C₉H₂₁AlO₃ (Sigma-Aldrich, Lot#MKCM4214, Code=102340685, purity ≥ 98%), sodium hydroxide NaOH (Fisher-Chemical, Lot1870577, Code=S/4920/60, purity=98.99%) and distilled water.

2.2. Catalyst synthesis

2.2.1. Synthesis protocol

Mixtures were prepared from clays (D1 or D2), sand (SM), sodium hydroxide, aluminum isopropoxide and water. The zeolite catalyst synthesis protocol, illustrated schematically in Fig.1., was inspired by the protocol of Reza Khoshbin and al, 2017[19]. This protocol consists of four parts, but for ease of use, we have modified it into two parts, I and II (See Fig.1). In addition to this modification, we applied a design of experiments methodology to this protocol. This is the Plackett and Burman (PB) design.

Fig.1. Schematic flow chart for preparation steps of catalysts.

2.2.2. Synthesis optimization

Optimization was performed using experimental designs. The design used was that of Plackett and Burman (PB). This is a screening design based on a first-order response surface model, for k factors (quantitative or qualitative) at two levels +1 and -1, in which interactions are not taken into account. The model equation is as follows [20]:

With the number N of trials (here a multiple of 4, $N = k+1$), \bar{y} is the mean, μ_i the effect of factors X_i and y the result of the experiment.

Table 1 below gives the characteristics and experimental ranges of the variable factors used for catalyst synthesis. In order to obtain catalysts with good catalytic characteristics, seven (7) factors were used : aluminum isopropoxide (X1), clay (X2), sand (X3), stirring time (X4), drying time (X5), calcination temperature (X6) and calcination time (X7). These factors were chosen, on the one hand, on the basis of the results of preliminary analyses of clays (D1 and D2) and sand (SM) and, on the other hand, on the basis of literature data.

Table.1 Experimental domain.

Factors

Symbol

-1

+1

Aluminum Isopropoxide (IP)

X1

1g

2g

Clay (D)

X2

Raw clay (D1)

Activated clay (D2)

Sand (SM)

X3

18 μm (SM1)

24 μm (SM2)

Agitation Time (TA)

X4

6h

10h

Drying Time (TS)

X5

12h

24h

Calcination temperature ($T^{\circ}\text{C}$)

X6

550 $^{\circ}\text{C}$

650 $^{\circ}\text{C}$

Calcination Time (TC)

X7

3h

4h

Next, eight (8) trials were carried out, based on the construction principle of Hadamard's experiment matrix (Table 2) [21]. This matrix is constructed from the sequence of + and - signs corresponding to the +1 and -1 level of the first row[20]. Hadamard's design is often used first to screen factors in order to obtain an initial assessment of their influence on the desired response, based on a reduced number of tests to be carried out in the Lab.

Table2. Hadamard matrix.

N° Exp

Coded values

X1

X2

X3

X4

X5

X6

X7

1

+1

-1

+1

+1

-1

-1

+1

2

+1

+1

-1

+1

+1

-1

-1

3

-1

+1

+1

-1

+1

+1

-1

4

-1

-1

+1

+1

-1

+1

+1

5

+1

-1

-1

+1

+1

-1

+1

6

+1

+1

-1
-1
+1
+1
-1
7
-1
+1
+1
-1
-1
+1
+1
8
-1
-1
-1
-1
-1
-1
-1
-1

After replacing the coded values with real values, the following Table 3 shows the experimental design.

Table.3Experimentation plan.

CAZ

IP(g)

D (g)

SM (μm)

TA (h)

TS (h)

(T°C)

TC (h)

1

2

D1

SM2

10

12

550

4

2

2

D2

SM1

10

24

550

3

3

1

D2

SM2

6

24

650

3

4

1

D1

SM2

10

12

650

4

5

2

D1

SM1

10

24

550

4

6

2

D2

SM1

6

24

650

3

7

1

D2

SM2

6

12

650

4

8

1

D1

SM1

6

12

550

3

The synthesis technique involved first preparing a gel precursor by mixing two solutions A (slurry) and B (Part-I/Fig.1). Slurry A is a mixture of 20g clays (D1 or D2), SM Sand (SM1 = 18 μm or SM2 = 24 μm) and distilled water (129 ml). Slurry B is a mixture of 4g NaOH, 1 or 2g aluminum isopropoxide and 141 ml distilled water. Next, hydrothermal synthesis (Part-II/Fig.1) began after mixing solutions A and B. This mixture yielded an aluminosilicate gel. The latter was homogenized and stirred for 6 to 10 hours before being filtered and dried at 105°C for 12 to 24 hours in an oven, resulting in a solid. This was calcined at 550 or 650°C for 3 to 4 hours. Any carbonization residues were removed by thorough washing with distilled water until a pH close to neutrality was obtained. The resulting materials were cooled, dried and ground to a particle size (\emptyset) of 18 μm . These materials constitute our zeolite catalysts. The completion of these eight (8) experiments resulted in eight (8) corresponding zeolite catalysts.

Zeolite catalysts are characterized by their activity, which is essentially related to surface acidity[22]. A surface acidity or Surface Function (SF) test was carried out on the catalysts.

The result of this test is called the Yexp response.

Determination and quantification of catalyst surface functions was carried out using the BOEHM titration method[23]. This method enables functional groups with a range of acidities or basicities to be assayed with bases or acids respectively. The protocol used was as follows: a mass of 0.5 g of CAZs was brought into contact for 72 h, with stirring, in a 100 mL beaker, with 25 mL each of 0.1 N aqueous solutions of NaOH, NaHCO₃, Na₂CO₃ (determination of acid groups) and HCl (determination of basic groups) to ensure that as many of the catalyst surface groups as possible were reacted, then the mixture was filtered through Whatman paper (0.45 micron).

After filtration, titration of excess solutions was carried out using 0.1 N sodium hydroxide and hydrochloric acid solutions for the basic and acid functions respectively. The basic solutions were titrated with 0.1 N hydrochloric acid (HCl), using three (3) drops each of phenolphthalein, helianthin and bromothymol blue, and the acid solution with 0.1 N sodium hydroxide (NaOH), with phenolphthalein as the color indicator. Since this is a back assay, the number of moles of the desired function is equivalent to the number of moles reacted with the contact solution. Quantification of acidic and basic groups is performed using the following formula:

Where

n (reacts) : quantity of material (acid or base) reacted (meq);

m (CAZ) : mass of catalyst (g).

The results obtained were processed using Nemrod software (version 9901 French, LPRAI-Marseille Inc., France) for factor screening. The factor significance test was performed by calculating the experimental error (Equations (3) and (4)).

and

Where

is the experimental error, σ is the standard deviation, N is the number of repetitions, p is the number of coefficients, Y_i is the experimental response and \hat{Y}_i is the response predicted

by the model.

The following equation (5) was used to calculate the contribution of each factor to the acidity of the synthesized zeolite catalysts [21].

Where

P_i: is the contribution of factor i to the response;

b_i : the statistical coefficient corresponding to factor i.

For further work, three (3) best zeolite catalysts (CAZ) were selected on the basis of their surface acidity (Y_{exp}). These catalysts were characterized.

2.3. Catalyst characterization

X-ray diffraction (XRD) on the three (3) catalysts was performed using an ANCHOR SCAN version "1.0" diffractometer at Ahmed Bello University (ABU) in the Federal Republic of Nigeria. The scan range was 5.02 to 75.97° in 0.02° increments over a period of 29.07 seconds; Cu counterelectrode; 45 kV-40mA.

X-ray fluorescence (FRX) was carried out using a THERMO-SCIENTIFIC Newton XL3t at the Geology Laboratory of the Centre d'Excellence Africain en Mines et Environnement Minier (CEA-MEM) at INP-HB, Yamoussoukro, Côte d'Ivoire, to determine the elemental mineralogical composition of the catalyst samples. Measurements in "MINING" mode, in the 2θ range for 120 min, were carried out on an accessory fitted with an RFID (Radio Frequency Identification) chip, enabling the analyzer to detect it automatically and convert it into a benchtop analyzer. A measuring stand called a safety cord is used to prevent the operator from coming into contact with the X-rays emitted by the FRX device. Data transfer was carried out directly on the computer using a powerful reader called Niton XL3t coupled with NDF software. The "Silica Alumina Ratio" (SAR) of the catalysts were obtained using equation (6).

Where

= Molar mass of silicon ;

- = Molar mass of aluminium;
- = Molar mass of silicon oxide;
- = Molar mass of aluminum oxide;
- = Silicon oxide constant ;
- = Aluminum oxide constant;
- = SiO₂ content of the sample (obtained by FRX) ;
- = Al₂O₃ content of sample (obtained by FRX).

Infrared spectroscopy was carried out on the catalysts in ATR (Attenuated Total Reflectance) mode using a Bruker Alpha Fourier transform spectrometer equipped with a diamond crystal (refractive index of diamond: 2.451) in the wavelength range from 400 cm⁻¹ to 4000 cm⁻¹ with a spectral resolution of 4.0 cm⁻¹.

Measurements of the textural properties of the three catalysts were determined by the Brunauer, Emmet and Teller (B.E.T) method. This was carried out at ABU (Ahmed Bello University) in the Federal Republic of Nigeria, using a Quantachrome NovaWin-Data Acquisition and Reduction for NOVA instruments version 11.03. Catalyst samples were degassed at 150°C and 250°C for ≈ 3 hours.

Adsorption and desorption processes are monitored by measuring the change in thermal conductivity of a gas stream composed of 99.99% nitrogen (adsorbate) and 70% 99.99% helium (carrier gas).

Scanning Electron Microscopy (SEM) was carried out using the JEOLJ SM-5300. Catalyst samples were pre-coated with a thin layer of gold (between 20 and 30Å) to increase their electrical conductivity.

Thermogravimetric analysis (TGA) and differential thermal analysis (DTA) were carried out at the University of Kaduna in the Federal Republic of Nigeria, using a PerkinElmer TGA-4000 instrument manufactured in the Netherlands.

2.4. Catalytic cracking reaction

2.4.1. Microreactor characteristics

A microreactor was specially designed for catalytic cracking operations at the ESI (Higher School of Industry) mechanical engineering workshop at INP-HB. The 10 cm³ microreactor was obtained using equations (7) and (8):

Where

Sb: Base area;

H: height of the microreactor (for $V \approx 9.9 \text{ cm}^3 \approx 10 \text{ cm}^3$, $H \approx 12.5 \text{ cm}$);

R: Radius of the microreactor (for $H = 12.5 \text{ cm}$, $R \approx 0.5 \text{ cm}$ and therefore $D \approx 1 \text{ cm}$).

D: Diameter of the microreactor.

As the microreactor is made of steel, which has a melting point between 1400°C and 1500°C, it can withstand temperatures above 500°C and pressures between 1 and 3 bar.

2.4.2. Description of the cracking plant

Fig. 2 shows the model used for catalytic cracking of naphtha on the three best CAZs: CAZ-1, CAZ-2, and CAZ-7.

Fig. 2. Model of the cracking plant (Design: SolidWorks software).

(1): Pressure gauge

(2): Power supply

(3): Microreactor

(4): Oven

(5): Conductive wire connecting the oven to the temperature controller

(6): Temperature controller

(7): Temperature controller support.

Naphtha cracking occurred under mild conditions. The operating conditions considered were as follows:

- Reaction temperatures: 250°C;
- pressure: atmospheric (1 atm);
- Residence time: 60s;
- Microreactor quenching time: 1h;
- Spatial velocity (PPH): 1 h⁻¹ (injection using a syringe).

PPH is defined as the ratio of the feed's mass flow rate to the catalyst's mass [24].

2.4.4. Cracking procedure

To perform the cracking operation, 0.3 g of CAZ is placed in the microreactor. Then, the microreactor is inserted into the electric furnace, and the temperature is raised in 50°C increments until it reaches 250°C. After ensuring the installation is airtight, 5 mL of naphtha (3.06 g) is injected into the microreactor as the feedstock. The oven temperature is controlled using an automatic regulator, and the reactor temperature is monitored with a K/J type probe thermometer. Finally, the cracking products leaving the microreactor are cooled for one hour in cold water at approximately 0°C and then weighed. Note that thermal control cracking (without catalyst) and a repeat reaction (catalytic reaction) were carried out for the catalytic cracking reaction.

The X_i yields (equation (9)) were calculated by dividing the mass of the product obtained after cracking (m_0) by the mass introduced into the reactor (m_i).

The rate of increase of the proportion of light molecules, denoted T_a (equation (10)), was calculated using the following formula:

Where

P_d is the difference in proportions between CT and CC. P_t is the proportion of all light molecules that have increased. The products obtained after catalytic cracking are characterized by GC-MS.

3. Results and Discussion

3.1. Plackett-Burman design

Table 4 below shows the experimental design and the Y_{exp} response values, which were calculated using equation (3). It also shows the experimental error, $2\sigma_e$.

Table .4 Experimental results obtained for catalysts according to Hadamard's plan.

Factors

N°Exp

CAZ

true values

Y_{exp} (meq/g)

U1 (g)

U2

U3 (μm)

U4 (h)

U5 (h)

U6 (°C)

U7 (h)

1

CAZ-1

2

D1

24

10

12

550

4

65

2

CAZ-2

2

D2

18

10

24

550

3

60

3

CAZ-3

1

D2

24

6

24

650

3

15

4

CAZ-4

1

D1

24

10

12

650

4

50

5

CAZ-5

2

D1

18

10

24

550

4

35

6

CAZ-6

2

D2

18

6

24

650

3

50

7

CAZ-7

1

D2

24

6

12

650

4

55

8

CAZ-8

1

D1

18

6

12

550

3

20

Experimental error $2\sigma_e$

5.76

Fig. 3 shows the estimated coefficients and their statistics.

Fig. 3. Estimates and coefficient statistics.

A significance test was performed on each coefficient in the model based on the criterion that a coefficient is statistically significant if its absolute value is greater than or equal to twice the experimental error [21]. The experimental standard deviation σ_e 2.88 was determined by repeating the test five times (Exp No1). Since there are two categories of factors (qualitative and quantitative), the value of the experimental error ($2\sigma_e$) is 5.76.

Based on this rule, the significant factors in this experiment are aluminum isopropoxide (IP), clay (D), stirring time (TA), drying time (TS), and calcination temperature ($T^\circ\text{C}$). Sand (SM) and calcination time (TC) are non-significant factors.

As shown in Table 4, surface acidity varies from 15 to 65 milliequivalents per gram (meq/g). By analyzing the significant factors in Fig. 3, we can see that surface acidity is low (15 meq/g) when D2 clay is used as a matrix with one gram of IP (1 g), a six-hour stirring

time, a 24-hour drying time, and a 650°C calcination temperature. Conversely, using the same D2 clay with two grams of IP, a stirring time of ten hours, a drying time of twenty-four hours, and a calcination temperature of 550°C results in higher surface acidity (65 meq/g). This improvement in surface acidity (15 meq/g to 60 meq/g) could be explained not only by the amount of IP used, but also by the stirring time. Conversely, the surface acidity is low (20 meq/g) when using raw clay D1 as a matrix with one gram of IP, a six-hour stirring time, a 12-hour drying time, and a 550°C calcination temperature. However, when using the same raw clay D1 with two grams (2g) of aluminum isopropoxide (IP), a stirring time of 10 hours, a drying time of 12 hours, and a calcination temperature of 550°C, the surface acidity becomes very high (65 meq/g). This increase in surface acidity (from 20 meq/g to 65 meq/g) could also be explained by the difference in the amount of IP used and the stirring time.

The surface acidity values in Table 4 are similar to those reported by Oumarou et al. (2021), but significantly higher than the values of FCC zeolite catalysts (30 to 50 meq/g) reported by Ibarra et al., [25]. These recorded values were also compared with those of an industrial catalyst used by the Zinder Refining Company (SORAZ). The CAZ-1, CAZ-2, CAZ-4, CAZ-6, and CAZ-7 catalysts are superior in terms of surface acidity to the industrial catalysts used by SORAZ, which have a surface acidity of 40 meq/g.

Ultimately, to obtain a more active zeolite catalyst, depending on whether D1 or D2 is used as the synthesis support, it would be preferable to use two grams (2 g) of IP as an additive and a stirring time of 10 hours. Additionally, 24 µm sand, a 12-hour drying time, a 550°C calcination temperature, and a 4-hour calcination time would suffice.

Fig. 4 shows how the various factors contribute to the recorded Y_{exp} response.

Fig. 4. Contribution of Various Factors

Fig. 4 illustrates the impact of various factors on the acidity of the synthesized catalysts' surfaces. The contributions of aluminum isopropoxide (IP), clay (D), Goulbi-Maradi sand (SM), stirring time (TA), drying time (TS), calcination temperature ($T^{\circ}\text{C}$), and calcination time (TC) to surface acidity are 20.75, 20.75, 1.54, 13.89, 38.59, 4.28, and 0.17, respectively.

For the next stage of this study, the three best catalysts (CAZ-1, CAZ-2, and CAZ-7) were selected based on surface acidity. The catalysts were characterized using XRD, XRF, IR, BET, SEM, and TDA-ATG methods.

3.2. Characteristics of CAZ-1, 2, and 7 Catalysts

3.2.1. X-ray diffraction (XRD)

Fig. 5 below shows the XRD analysis results for the three catalysts.

Fig. 5. X-ray diffractogram of CAZ-1, CAZ-2 and CAZ-7 catalysts.

Observing the diffractograms of the three catalysts (Fig. 5) reveals the disappearance of all the characteristic peaks of kaolinite [18] and confirms their transformation into métakaolinite [26,27]. According to K. Traoré [28], at temperatures above 500°C , kaolinite ($\text{Al}_2\text{O}_3 \cdot 2\text{SiO}_2 \cdot 2\text{H}_2\text{O}$) loses its hydroxyl (OH) function and transforms into metakaolinite ($\text{Al}_2\text{O}_3 \cdot 2\text{SiO}_2$). The transformation of kaolinite into metakaolinite (metakaolinitization) can be explained by the fact that the catalysts were calcined prior to XRD analysis. The results of the experimental plan indicate that CAZ-1 and CAZ-2 were calcined at 550°C , while CAZ-7 was calcined at 650°C . However, according to authors Murat and A. Bachiorrini [29], the metakaolinite phase is the most reactive in the series of thermal transformations of kaolinite. These destroyed clay minerals give way to peaks characteristic of quartz (SiO_2).

This can be explained by the effective incorporation of silica (SiO_2) during the synthesis of the catalysts.

Observation of the diffractograms of the three catalysts reveals intense, well-resolved peaks. For CAZ-1, the peaks appear around 21.07° , 26.67° , and 36.80° . For CAZ-2, the peaks appear around 20.80° , 26.67° , and 36.55° . For CAZ-7, the peaks are visible at 20.82° , 26.67° , and 36.55° . These intense peaks are similar to those of standard, perfectly crystalline zeolite-Y (100% crystallinity), as analyzed by XRD in the range of $5.018^\circ(2\theta)$ to $69.966^\circ(2\theta)$ with a step size of 0.026° . This highly crystalline zeolite standard exhibits peak intensities characteristic of reflections 511, 440, and 642, which correspond to 20.5° , 26.5° , and 35° , respectively [30].

The peaks of the highly crystalline standard zeolite are similar to the intense, well-resolved peaks of our three synthesized zeolite catalysts (CAZ-1, CAZ-2, and CAZ-7).

3.2.2.X-ray fluorescence (XRF)

The three best synthesized CAZ-1, CAZ-2, and CAZ-7 catalysts were analyzed using the XRF method. The results are grouped in Table 5.

Table.5Chemical composition, $\text{SiO}_2/\text{Al}_2\text{O}_3$ and Si/Al ratios of CAZ-1, 2 and 7.

Oxides (%)

CAZ-1

CAZ-2

CAZ-7

SiO_2

74.67

64.94

65

Al_2O_3

12.16

17.19

17.65

Fe₂O₃

3.44

8.35

7.62

MgO

2.88

2.98

1.94

P₂O₅

0.22

0.18

0.19

SO₃

0.21

0.05

0.05

TiO₂

0.66

0.76

0.73

MnO

0.29

0.47

0.44

CaO

0.60

1.21

1.10

K₂O

1.17

0.89

0.78

Na₂O

0.85

0.45

0.39

ZrO₂

0.14

0.03

0.03

Autres

2.71

2.5

4.08

SiO₂/Al₂O₃

6.14

3.77

3.68

Si/Al

5.33

3.27

3.19

As shown in Table 5, there was a considerable increase in SiO₂ content and a significant decrease in Al₂O₃ content across all catalyst samples. SiO₂ content increased from 58.851% in the D1 zeolite catalyst synthesis support to 74.67% in CAZ-1. Similarly, it

increased from 42.88% in D2 to 64.94% in CAZ-2 and 65% in CAZ-7. This increase can be attributed to the addition of SM sand (SiO_2) during zeolite catalyst synthesis. According to Otmani's work[31], silica confers good mechanical strength [31]to catalysts and increases their acidity[32] for catalytic cracking operations. Furthermore, the SiO_2 content of all the synthesized catalysts (CAZ-1, CAZ-2, and CAZ-7) is higher than that of the commercial fluid catalytic cracking (FCC) catalyst ($\text{SiO}_2 = 54.1\%$) used by Hussain et al. (2015) [33]in the catalytic cracking of vacuum gas oil, as well as that of the ZSM-5 catalysts ($\text{SiO}_2 = 57.12\%$) synthesized by Y. Ghrib et al. (2015)[34]from metakaolinite.

The SiO_2 and Al_2O_3 contents result in silica alumina ratios (SAR) of 5.33 for CAZ-1, 3.27 for CAZ-2, and 3.19 for CAZ-7. CAZ-1's SAR falls within the zeolite-Y range (Si/Al: 3.5–5.5)[35], while CAZ-2's and CAZ-7's SARs fall within the intermediate zeolite-Y range (Si/Al: 2–5)[36].

3.2.3. Fourier Transform Infrared Spectroscopy (FTIR)

Fourier Transform Infrared (FT-IR) spectroscopy was performed to detect chemical functions on the surfaces of three zeolite catalysts. The observed bands were assigned using data from the literature. The results of this analysis are shown in Fig. 6.

Fig. 6. TF-IR spectrum of CAZ-1, CAZ-2 and CAZ-7 catalysts from 4000 to 400 Cm^{-1} .

Fig. 6 shows the infrared (IR) spectra of the three synthesized zeolite catalysts: CAZ-1, CAZ-2, and CAZ-7. The IR spectra of CAZ-2 and CAZ-7 show bands appearing at 689 and 693 cm^{-1} , respectively. These bands are attributed to the stretching vibrations of the symmetric and asymmetric T-O-T (T = Si or Al) bonds of the internal tetrahedra (SiO_4 and AlO_4) of the CAZ-2 and CAZ-7 catalysts[37]. According to Ahmad Asghari et al. (2019), this T-O-T structure is specific to zeolite catalysts [38].

The bands that appear at 775 cm^{-1} on the FT-IR spectra of CAZ-1 and CAZ-7 are attributed to the stretching of the framework of the siliceous materials and the conversion of the octahedral coordination of kaolinite (Al^{3+}) to the tetrahedral coordination of métakaolinite [39,40]. This conversion is explained by the temperature and calcination time during synthesis of these zeolite catalysts[10]. The peaks at 984 cm^{-1} on the FT-IR

spectrum of CAZ-1, 991 cm^{-1} on the FT-IR spectrum of CAZ-2, and 998 cm^{-1} on the FT-IR spectrum of CAZ-7 correspond to aluminosilicate vibrations[41]. The shoulder peaks appearing at 1539 and 1651 cm^{-1} on the FT-IR spectrum of CAZ-2 are attributed to stretching of the external asymmetry of the Si-O-Si bond. The bands observed at 3671 and 3630 cm^{-1} on the FT-IR spectra of CAZ-2 and CAZ-7, respectively, are related to the stretching vibrations of the hydroxyl groups (Al-OH) on the inner surface and the stretching vibrations of the inner hydroxyl groups [38,42].

3.2.4. Specific surface area, pore volume and pore diameter of CAZ

The specific surface areas (SBET, S_{micro} and S_{meso}), pore volumes (V_{micro} and V_{meso}) and pore diameters (D_{micro} and D_{meso}) of the three best catalysts (CAZ-1, CAZ-2 and CAZ-7) synthesized were evaluated. The BET specific surface area (SBET) was evaluated using the BET method, and the specific surface areas of micropores (S_{micro}) and mesopores (S_{meso}) and the volume of micropores (V_{micro}) were evaluated using the t-plot method. The mesopore volumes (V_{meso}) and mesopore diameters (D_{meso}) were evaluated using the BJH method. The micropore diameter (D_{micro}) was evaluated using the HK method. Micropore diameter (D_{micro}) was assessed using the HK method. The experimental results of all these analyses are presented in the following Table 6.

Table.6 Specific surface area, pore volume and pore diameter of CAZ-1, 2 and 7.

CAZ

SBET

(m^2/g)

Surface Spécifique

Volume des pores

Diamètre des pores

S_{micro}

(m²/g)

Sméso

(m²/g)

Vmicro

(Cm³/g)

Vméso

(Cm³/g)

Dmicro

(nm)

Dméso

(nm)

CAZ-1

190.04

195.20

190

0.02

0.09

1.84

2.15

CAZ-2

260.90

299.30

260.90

0.04

0.16

0.36

2.14

CAZ-7

322

346.80

322

0.05

0.17

1.84

2.13

The results show that the specific surface areas (SBET and S_{meso}) of CAZ-2 and CAZ-7 are equal after synthesis. However, they increased during alkaline treatment with NaOH, the addition of sand (SM), and the addition of aluminum isopropoxide (IP), as well as during calcination. Based on the D2 support used for the synthesis of CAZ-2 and 7 (256.30 m²/g), the SBET and S_{meso} increased from 256.30 to 260.90 m²/g and from 256.30 to 322 m²/g, respectively. According to L. J. He et al., 2017 [43] and Z. Zhang et al., 2014 [44], this increase reflects an increase in mesoporosity during synthesis, which can be explained by an increase in calcination temperature. The development of microporosity in CAZ-2 and CAZ-7 can be explained by an increase in the specific surface area of micropores (S_{micro}). Thus, the specific surface areas of micropores (S_{micro}) increase from 260.90 m²/g to 299.30 m²/g for CAZ-2, and those of mesopores (S_{meso}) increase from 322.00 m²/g to 346.80 m²/g for CAZ-7. Furthermore, these specific surface area results for the CAZ-2 and CAZ-7 catalysts are higher than those for the commercial FCC catalysts used by Ribeiro et al., 2013 [45] in their work evaluating the efficiency of commercial FCC catalysts. Similarly, the specific surface area results for our CAZ-2 and CAZ-7 catalysts are higher than those obtained by Y. Yue et al., 2018 (SBET = 292 m²/g, S_{micro} = 224 m²/g, and S_{meso} = 68 m²/g) when synthesizing ZSM-5 zeolite catalysts using silicon-rich diatomite and aluminum-rich rectorite [6]. However, the specific surface area of CAZ-1 decreased considerably after synthesis from 446.50 m²/g (D1) to a virtually constant value (SBET = 190.04 m²/g, S_{micro} = 195.20 m²/g, and S_{meso} = 190.00 m²/g). This can be

explained by the presence of impurities (carbonates, organic matter, etc.) in the D1 synthesis medium of CAZ-1 catalysts, as reported by E.A. Amam[46].

A comparable trend to that of the specific surface areas of CAZ-2 and CAZ-7 was observed for the mesopore diameter(D_{meso}) and micropore diameter(D_{micro}) diameters of the same catalysts. Thus, D_{meso} increased from 2.13 nm (CAZ-7) with a hydrothermal treatment time of 6 hours to 2.14 nm (CAZ-2) with a treatment time of 10 hours. However, the micropore diameter of the CAZ-2 and CAZ-7 catalysts decreased from 1.84 nm (CAZ-7) after 6 hours to 0.36 nm (CAZ-2) after 10 hours. I. Qoniah et al., 2015 also observed an increase in mesopore diameter and a decrease in micropore diameter as a function of stirring time in their work on the direct synthesis of mesoporous ZSM-5 zeolite catalysts using kaolinite clay from Indonesia [16]. This shows that a long period of hydrothermal treatment promotes the formation of mesoporous structures in the framework of zeolite catalysts[47].

Similar to the D_{micro} of CAZ-2 and CAZ-7, a trend was observed in the mesopore volume(V_{meso}) and micropore volume(V_{micro}) volumes of the CAZ-2 and CAZ-7 catalysts. Thus, V_{meso} decreased from 0.17 cm³/g (CAZ-7) with a 6-hour hydrothermal treatment to 0.16 cm³/g (CAZ-2) with a 10-hour hydrothermal treatment. The V_{micro} of the catalysts decreased slightly, from 0.05 cm³/g (CAZ-7) at 6 hours to 0.04 cm³/g (CAZ-2) at 10 hours. H. Jia et al., 2021[48]; also observed a decrease in the volume of micropores during their work on the hydrothermal synthesis of ZSM-5 zeolite catalysts.

3.2.5. Scanning Electron Microscopy (SEM)

Scanning Electron Microscopy (SEM) was performed on the three (3) zeolite catalysts (CAZ-1, CAZ-2, and CAZ-7). The images obtained are shown in Figs. 7(a), 7(b) and 7(c) for CAZ-1, CAZ-2 and CAZ-7, respectively.

Fig. 7. SEM images of CAZ-1 (a), 2 (b) and 7 (c) at 50 μ m magnification.

Fig. 7 shows scanning electron microscope (SEM) images of three zeolite catalysts: CAZ-1, CAZ-2, and CAZ-7. All three catalysts—CAZ-1 (Fig. 7a), CAZ-2 (Fig. 7b), and

CAZ-7 (Fig. 7c) feature tetrahedra (TO_4) and hexagonal prisms, which are characteristic of Y-type zeolite catalyst morphology [48,49]. These structures contribute to the formation of α -cavities (supercages) and β -cavities (sodalites), which are specific to zeolite-Y [50]. The crystallinity of CAZ-1, CAZ-2, and CAZ-7 reached a level similar to that of zeolite-Y, which has a highly crystalline structure, i.e., well-defined tetrahedral and/or prismatic crystals [51]. This is due to a fairly favorable stirring time (hydrothermal synthesis), which is 10 hours for CAZ-1 and CAZ-2 and 6 hours for CAZ-7 (Table 4).

This is in line with the observations of A.S. Kovo et al., 2009 [49], who reported that no zeolite catalyst formation can be obtained after three (3) hours of crystallization. This indicates that CAZ formation has not begun. Using stirring times longer than three hours (six and ten hours) during the synthesis of our three zeolite catalysts produced well-crystallized catalysts comparable to the highly crystalline standard zeolite-Y model.

3.2.6. Gravimetric Thermal Analysis (GTA)/Differential Thermal Analysis (DTA)

To study the thermochemical behavior of the synthesized CAZ-1, CAZ-2, and CAZ-7, Differential Thermal Analysis (DTA) and Differential Scanning Calorimetry (DSC) were performed. Figs 8, 9, and 10 below show the DTA and DSC results obtained with CAZ-1, CAZ-2, and CAZ-7.

Fig. 8. TDA and TGA curves for CAZ-1.

Fig. 8 corresponds to the ATD isotherm of CAZ-1 and shows three main peaks. A first moderately intense endothermic peak around 100°C , which could indicate the elimination of water by physisorption in the micropores and mesopores of CAZ-1. At this temperature, CAZ-1 experiences a mass loss of approximately 3.47%. A second, very intense endothermic peak occurs around 400°C and is attributable to the dihydroxylation of clay minerals. The mass loss value for CAZ-1 at this temperature is 4.61%. A third, less intense peak appears around 700°C , corresponding to the structural reorganization of CAZ-1. The associated mass loss value is 3.16%.

Fig. 9. TDA and TGA (b) curves for CAZ-2.

Fig. 9 illustrates the ATD isotherm of CAZ-2 and shows three endothermic peaks. The first is observed at around 100°C, is moderately intense, and also corresponds to the elimination of water by physisorption in the micro- and mesopores of CAZ-2. At this temperature, CAZ-2 experiences a mass loss of approximately 2.53%. A second, intense peak around 380°C reflects the dihydroxylation of clay minerals, such as kaolinite and illite. The mass loss value for CAZ-2 at this temperature is nearly zero. A third, moderately intense peak around 700°C corresponds to the structural reorganization of CAZ-2. The associated mass loss value for CAZ-2 is 1.37%.

Fig. 10. TDA and TGA curves for CAZ-7.

Fig. 10 shows the ATD isotherm curve for CAZ-7. Two peaks are visible: the first is an intense endothermic peak at approximately 480°C, which is due to dihydroxylation. The mass loss value for CAZ-7 at this temperature is virtually zero. A second, less intense peak around 650°C reflects the structural reorganization of CAZ-7. The associated mass loss value for CAZ-7 is 2.31%.

The thermogravimetric analysis results obtained for the synthesized zeolite catalysts are similar to those reported by Kabalan (2016) [52] in his thesis on synthesizing nanoporous materials for molecular decontamination and energy storage.

3.3. Rate of Increase in Light Molecule Proportions, Catalytic Yield, and Reaction

Mechanism of Catalytic Cracking with CAZ-1, 2, and 7.

Table 7 shows the percentage increase in the proportion of light molecules (Ta (%)),

Percent catalytic yields of catalysts 1, 2, and 7 (RCAZ-1, 2 et 7).

Table .7 The proportion of increase rates of molecules and catalytic cracking yields increases in the presence of CAZ-1, CAZ-2, and CAZ-7.

CAZ

variation in proportions

Yield

Explanation

Light molecules whose proportions have increased.

Ta (%)

RCAZ-1, 2 and 7 (%)

CAZ-1

Cyclohexane, 2-methylhexane, 3-methylhexane, etc.

5

69.93%

Decrease: 5,6-dimethylundecane (13-CA).

CAZ-2

N-octane, 2,2-dimethylheptane, etc.

10.85

83

Decrease: 3,5,5-trimethyl-1-hexene (11-CA).

CAZ-7

5,6-Dimethylundecane, 3-methylheptane, etc.

8.70

50.6

Decrease: 2,6-Dimethylnonane (11-CA)

CA : Carbon Atom.

It should be noted that CAZ-1 catalysts promoted a 5% increase in light molecules (Ta) through the catalytic cracking of naphtha. These molecules include those with six carbon atoms, such as cyclohexane, and those with seven carbon atoms, such as 2-methylhexane, 3-methylhexane, and n-heptane. However, CAZ-1 reduces longer molecules, such as 5,6-dimethylundecane, which has thirteen carbon atoms. This can be explained by the reaction mechanism shown in Fig. 11. The n-hexane molecule undergoes dehydrocyclization^[53] to produce cyclohexane. The naphtha cracking yield in the presence of CAZ-1, denoted RCAZ-1, is 69.93%.

Fig. 11. A proposal for a reaction mechanism to obtain 2-methylhexane, 3-methylhexane and cyclohexane from 5,6-dimethylundecane, using CAZ-1 as a catalyst.

CAZ-2 influences the catalytic cracking of naphtha, increasing the percentage of light molecules to 10.85%. As well as increasing the percentage of light molecules with six (cyclohexane) and seven (2-methylhexane, 3-methylhexane and n-heptane) carbon atoms, CAZ-2 also induced an increase in molecules with eight (n-octane) and nine (2,2-dimethylheptane) carbon atoms. This increase is likely due to a decrease in the percentage of a molecule with eleven (11) carbon atoms: 3,5,5-dimethyl-1-hexene. This phenomenon can be explained by the reaction mechanism shown in Fig. 12. The cracking yield in the presence of CAZ-2 (denoted RCAZ-2) is 83%.

Fig. 12. A proposal for a reaction mechanism to obtain 2,2-dimethylheptane and n-octane from 3,5,5-trimethyl-1-hexene, using CAZ-2 as a catalyst.

Similar to CAZ-1 and CAZ-2, CAZ-7 impacted the catalytic cracking of naphtha, increasing the proportion of light molecules to 8.70%. Unlike CAZ-1 and CAZ-2, which promoted a decrease in the proportion of 5,6-dimethylundecane, CAZ-7 promoted an increase in this molecule's percentage. The reaction mechanism (Fig. 13) below would explain the increases in 5,6-dimethylundecane and 3-methylheptane from 2,6-dimethylnonane. This mechanism was proposed based on several mechanisms found in the literature. The 2,6-dimethylnonane molecule undergoes protonation (proton transfer from CAZ-1 to the molecule), resulting in a carbocation ion. This ion then undergoes C-C bond cleavage to produce 3-methylheptane (formed via rapid rearrangement through alkyl skipping from 4-methylheptane) and an allylic carbocation ion. This ion then donates a proton to CAZ-7 (deprotonation), forming propene. The propene then undergoes further protonation to form propane. The propane then undergoes isomerisation with the n-decane molecule in the reaction medium to form n-tridecane. The latter undergoes very rapid rearrangement via alkyl jumps (or hydride jumps) to form 5,6-dimethylnonane. The yield of catalytic cracking in the presence of CAZ-7 (RCAZ-7) is 50.62%.

Fig. 13. A proposal for a reaction mechanism to obtain 5,6-dimethylundecane and 3-methylheptane from 2,6-dimethylnonane, using CAZ-7 as a catalyst.

These three reaction mechanisms show that CAZ-1, CAZ-2, and CAZ-7 favored the production of alkanes and cycloalkanes. This leads us to conclude that these synthesized zeolite catalysts are likely to be zeolite-Y type zeolite catalysts. This was also corroborated by Pigot [54], who reported that these types of zeolite favor the production of n-alkanes, isoparaffins, and even cycloalkanes rather than alkenes. According to Krijn P. J et al., 2010 [55] this particular selectivity can be explained by mesoporosity.

Indeed, a zeolite-Y containing mainly mesopores and a few micropores produces medium cuts ranging from C11 to C15. The results of the GC-MS analysis of the catalytic cracking

products of naphtha on CAZ-1, 2 and 7 confirm those of the BET analysis (Table 6). CAZ-7, which has more mesopores than CAZ-1 and 2, favored the production of 5,6-dimethylundecane, a molecule containing thirteen carbon atoms.

4. Conclusion

X-ray diffraction analyses of the three zeolite catalysts (CAZ-1, CAZ-2, and CAZ-7) show a disappearance of the kaolinite, illite, and smectite peaks. This gives way to significant quartz (SiO_2) peaks, reflecting the incorporation of silica-rich sand (SM) used in synthesizing these zeolite catalysts. Additionally, the diffractograms of the three catalysts exhibit intense, well-resolved peaks that resemble those of highly crystalline zeolite Y standards.

X-ray fluorescence (XRF) analysis yielded SiO_2 and Al_2O_3 content values that correspond to Silica Alumina Ratios (SAR) of 5.33 for CAZ-1, 3.27 for CAZ-2, and 3.19 for CAZ-7. The SAR of CAZ-1 belongs to the SAR range of zeolite-Y, while the SARs of CAZ-2 and CAZ-7 belong to the SAR range of intermediate zeolite-Y. IR analysis of CAZ-1, 2, and 7 shows characteristic bands of symmetric and asymmetric T-O-T (T = Si or Al) bond vibrations of SiO_4 and AlO_4 tetrahedra characteristic of zeolite structures. Peaks corresponding to aluminosilicate vibrations and to the stretching of the external asymmetry of the Si-O-Si bond were observed in the IR spectra of the synthesized zeolite catalysts. Peaks were also observed that are attributed to the external stretching of the silica framework and the conversion of the octahedral coordination of kaolinite (Al^{3+}) to the tetrahedral coordination of metakaolinite. BET analysis of CAZ-2 and CAZ-7 shows an increase in specific surface area (SBET), micropores (S_{micro}), and mesopores (S_{meso}). This reflects an increase in micro- and mesoporousness during the synthesis of CAZ-2 and CAZ-7. In contrast, a decrease in BET specific surface area was observed during the synthesis of CAZ-1. A comparable trend to that of the specific surface areas of the synthesized catalysts was observed for pore diameters (D_{meso} and D_{micro}) and pore volumes (V_{meso} and V_{micro}). Nitrogen (N_2) desorption reveals a mixture of micro- and mesopores in the three uniformly distributed catalyst samples. Scanning Electron Microscopy (SEM) analysis of

the three samples reveals the presence of tetrahedra (TO_4) and hexagonal prisms, which are characteristic of zeolite catalyst morphology. This morphology contributes to the formation of α -cavities (supercages) and β -cavities (sodalites), which are characteristic of zeolite Y. The study of the thermochemical behavior of the synthesized catalysts made it possible, first, to determine initial peaks at around 100°C for all three (3) catalysts. This can be explained by the elimination of water from the surface of the catalysts. At these temperatures, the mass loss is approximately 3.47% for CAZ-1, approximately 2.53% for CAZ-2, and approximately 9.24% for CAZ-7. Next are the second peaks, which are visible at approximately 400°C for CAZ-1, 380°C for CAZ-2, and 480°C for CAZ-7. These peaks are due to the dihydroxylation reaction of clay minerals. The mass loss value at these temperatures is almost zero for CAZ-2 and CAZ-7. However, the mass loss value for CAZ-1 at 400°C is 4.61%. The third peaks correspond to the structural reorganization of the synthesized zeolite catalysts, with values of 700°C for CAZ-1 and CAZ-2 and 650°C for CAZ-7. The associated mass loss values are 3.16%, 1.37%, and 2.31%, respectively. The synthesized zeolite catalysts CAZ-1, CAZ-2, and CAZ-7 exhibit similar mineralogical, chemical, physical, morphological, and thermal characteristics to FAU-Y or Y zeolite catalysts. The latter promotes the selectivity of n-alkanes, isoparaffins, and cycloalkanes over alkenes.

References

- [1] N.E.R. Zimmermann, M. Haranczyk, History and Utility of Zeolite Framework-Type Discovery from a Data-Science Perspective, *Crystal Growth & Design* 16 (2016) 3043–3048. <https://doi.org/10.1021/acs.cgd.6b00272>.
- [2] T.F. Degnan, G.K. Chitnis, P.H. Schipper, History of ZSM-5 fluid catalytic cracking additive development at Mobil, *Microporous and Mesoporous Materials* 35–36 (2000) 245–252. [https://doi.org/10.1016/S1387-1811\(99\)00225-5](https://doi.org/10.1016/S1387-1811(99)00225-5).
- [3] K. Margeta, A. Farkaš, Introductory Chapter: Zeolites - From Discovery to New Applications on the Global Market, in: K. Margeta, A. Farkaš (Eds.), *Zeolites - New Challenges*, IntechOpen, 2020: p. 10. <https://doi.org/10.5772/intechopen.92907>.
- [4] J.N. Armor, A history of industrial catalysis, *Catalysis Today* 163 (2011) 3–9. <https://doi.org/10.1016/j.cattod.2009.11.019>.
- [5] T. Biligetü, Y. Wang, T. Nishitoba, R. Otomo, S. Park, H. Mochizuki, J.N. Kondo, T. Tatsumi, T. Yokoi, Al distribution and catalytic performance of ZSM-5 zeolites synthesized with various alcohols, *Journal of Catalysis* 353 (2017) 1–10. <https://doi.org/10.1016/j.jcat.2017.06.026>.
- [6] Y. Yue, Y. Kang, Y. Bai, L. Gu, H. Liu, J. Bao, T. Wang, P. Yuan, H. Zhu, Z. Bai, X. Bao, Seed-assisted, template-free synthesis of ZSM-5 zeolite from natural aluminosilicate minerals, *Applied Clay Science* 158 (2018) 177–185. <https://doi.org/10.1016/j.clay.2018.03.025>.
- [7] F. Pan, X. Lu, T. Wang, Y. Yan, Submicron ZSM-5 synthesized by green and fast route, *Materials Letters* 196 (2017) 245–247. <https://doi.org/10.1016/j.matlet.2017.03.060>.

- [8] X.-Y. Li, Y. Jiang, X.-Q. Liu, L.-Y. Shi, D.-Y. Zhang, L.-B. Sun, Direct Synthesis of Zeolites from a Natural Clay, Attapulgite, *ACS Sustainable Chem. Eng.* 5 (2017) 6124–6130. <https://doi.org/10.1021/acssuschemeng.7b01001>.
- [9] Y. Liu, S. Han, D. Guan, S. Chen, Y. Wu, Y. Yang, N. Jiang, Rapid green synthesis of ZSM-5 zeolite from leached illite clay, *Microporous and Mesoporous Materials* 280 (2019) 324–330. <https://doi.org/10.1016/j.micromeso.2019.02.027>.
- [10] Y. Yue, Y. Hu, P. Dong, X. Li, H. Liu, J. Bao, T. Wang, X. Bi, H. Zhu, P. Yuan, Z. Bai, X. Bao, Mesoscale depolymerization of natural rectorite mineral via a quasi-solid-phase approach for zeolite synthesis, *Chemical Engineering Science* 220 (2020) 115635. <https://doi.org/10.1016/j.ces.2020.115635>.
- [11] M. Wu, W. Jiang, J. Jiang, Y. Zou, P. Zhang, P. Mao, Y. Xu, Y. Shi, Synthesis of ZSM-5 zeolites using palygorskite as raw material under solvent-free conditions, *Bull Mater Sci* 43 (2020) 289. <https://doi.org/10.1007/s12034-020-02263-8>.
- [12] Y. Wang, H. Duan, Z. Tan, X. Meng, F.-S. Xiao, Illuminating solvent-free synthesis of zeolites, *Dalton Trans.* 49 (2020) 6939–6944. <https://doi.org/10.1039/D0DT00142B>.
- [13] Y. Ji, Y. Wang, B. Xie, F.-S. Xiao, Zeolite Seeds: Third Type of Structure Directing Agents in the Synthesis of Zeolites, *Comments on Inorganic Chemistry* 36 (2016) 1–16. <https://doi.org/10.1080/02603594.2015.1031375>.
- [14] X. Meng, F.-S. Xiao, Green Routes for Synthesis of Zeolites, *Chem. Rev.* 114 (2014) 1521–1543. <https://doi.org/10.1021/cr4001513>.
- [15] L. Zhang, Z. Bao, S. Xia, Q. Lu, K. Walters, Catalytic Pyrolysis of Biomass and Polymer Wastes, *Catalysts* 8 (2018) 659. <https://doi.org/10.3390/catal8120659>.
- [16] I. Qoniah, D. Prasetyoko, H. Bahruji, S. Triwahyono, A.A. Jalil, Suprpto, Hartati, T.E. Purbaningtias, Direct synthesis of mesoporous aluminosilicates from Indonesian kaolin clay without calcination, *Applied Clay Science* 118 (2015) 290–294. <https://doi.org/10.1016/j.clay.2015.10.007>.
- [17] O. Abdoulaye Dan Makaou, S. Gueu, M. Gourouza, K.B. Yao, Development of semi-synthetic catalyst based on clay and their use in catalytic cracking of petroleum residue,

Appl Petrochem Res 11 (2021) 147–154. <https://doi.org/10.1007/s13203-021-00268-w>.

[18] A.I. Abdourahmane, S. Gueu, M.A. Salam, H. Kone, K.B. Yao, Comparative study of physico-chemical, mineralogical and morphological characteristics of clay from Niger-Maradi: application to the synthesis of ZSM-5 aluminosilicate catalysts, (2022) 14.

[19] R. Khoshbin, R. Karimzadeh, Synthesis of mesoporous ZSM-5 from rice husk ash with ultrasound assisted alkali-treatment method used in catalytic cracking of light naphtha, *Advanced Powder Technology* 28 (2017) 1888–1897.

<https://doi.org/10.1016/j.appt.2017.04.024>.

[20] Plans d'expérience: constructions et analyses statistiques, Springer Berlin Heidelberg, Berlin, Heidelberg, 2010. <https://doi.org/10.1007/978-3-642-11472-4>.

[21] J. Goupy, L. Creighton, Introduction aux plans d'expériences, 3e éd, Dunod "L'Usine nouvelle," Paris, 2006.

[22] J.A. Rabo, G.J. Gajda, Acid Function in Zeolites: Recent Progress, in: D. Barthomeuf, E.G. Derouane, W. Hölderich (Eds.), *Guidelines for Mastering the Properties of Molecular Sieves*, Springer US, Boston, MA, 1990: pp. 273–297.

https://doi.org/10.1007/978-1-4684-5787-2_17.

[23] A. Contescu, C. Contescu, K. Putyera, J.A. Schwarz, Surface acidity of carbons characterized by their continuous pK distribution and Boehm titration, *Carbon* 35 (1997) 83–94. [https://doi.org/10.1016/S0008-6223\(96\)00125-X](https://doi.org/10.1016/S0008-6223(96)00125-X).

[24] P. Trambouze, Raffinage du pétrole Tome 4 - Matériels et équipements, Editions TECHNIP, 1999.

[25] Á. Ibarra, I. Hita, M.J. Azkoiti, J.M. Arandes, J. Bilbao, Catalytic cracking of raw bio-oil under FCC unit conditions over different zeolite-based catalysts, *Journal of Industrial and Engineering Chemistry* 78 (2019) 372–382. <https://doi.org/10.1016/j.jiec.2019.05.032>.

[26] F. Zibouche, N. Boudissa, A. Irekti, M.T. Abadlia, Géopolymérisation d'aluminosilicates. Influence des rapports Silice/Alumine, (n.d.).

[27] F. Zibouche, H. Kerdjoudj, J.-B. d'Espinose de Lacaillerie, H. Van Damme, Geopolymers from Algerian metakaolin. Influence of secondary minerals, *Applied Clay*

Science 43 (2009) 453–458. <https://doi.org/10.1016/j.clay.2008.11.001>.

[28] K. Traore, Frittage à basse température d'une argile kaolinique du Burkina Faso : transformations thermiques et réorganisations structurales = Low temperature sintering of a kaolinitic clay from Burkina Faso : Theermal transformations and structural reoganizations, Limoges, 2003.

[29] M. Murat, A. Bachiorrini, Corrélation entre l'état d'amorphisation et l'hydraulicité du métakaolin, Bulletin de Minéralogie 105 (1982) 543–555.
<https://doi.org/10.3406/bulmi.1982.7577>.

[30] Z. Qin, B. Shen, X. Gao, F. Lin, B. Wang, C. Xu, Mesoporous Y zeolite with homogeneous aluminum distribution obtained by sequential desilication–dealumination and its performance in the catalytic cracking of cumene and 1,3,5-triisopropylbenzene, Journal of Catalysis 278 (2011) 266–275. <https://doi.org/10.1016/j.jcat.2010.12.013>.

[31] S. Otmani, Valorisation des charges lourdes compoundées par le craquage catalytique, in: 2006: p. 88.

[32] P. Leprince, Le raffinage du pétrole - Tome 3 , Collectif Technip - Librairie Eyrolles, n.d.

[33] A.I. Hussain, A.M. Aitani, M. Kubů, J. Čejka, S. Al-Khattaf, Catalytic cracking of Arabian Light VGO over novel zeolites as FCC catalyst additives for maximizing propylene yield, Fuel 167 (2016) 226–239. <https://doi.org/10.1016/j.fuel.2015.11.065>.

[34] Y. Ghrib, N. Frini-Srasra, E. Srasra, Synthesis of ZSM-5 zeolite from metakaolinite: Effects of the SiO₂/Al₂O₃ molar ratio, the initial precursor and the presence of organic template agent, Surf. Engin. Appl.Electrochem. 53 (2017) 64–70.
<https://doi.org/10.3103/S1068375517010057>.

[35] A.W. Chester, E.G. Derouane, eds., Zeolite Chemistry and Catalysis, Springer Netherlands, Dordrecht, 2009. <https://doi.org/10.1007/978-1-4020-9678-5>.

[36] D.W. Breck, Zeolite molecular sieves: structure, chemistry, and use, New York, Wiley, 1973.

[37] L. Bouna, A. Ait El Fakir, A. Benlhachemi, K. Draoui, M. Ezahri, B. Bakiz, S. Villain, F.

Guinneton, N. Elalem, Synthesis and characterization of mesoporous geopolymer based on Moroccan kaolinite rich clay, *Applied Clay Science* 196 (2020) 105764.

<https://doi.org/10.1016/j.clay.2020.105764>.

[38] A. Asghari, M.K. Khorrami, S.H. Kazemi, Hierarchical H-ZSM5 zeolites based on natural kaolinite as a high-performance catalyst for methanol to aromatic hydrocarbons conversion, *Sci Rep* 9 (2019) 17526. <https://doi.org/10.1038/s41598-019-54089-y>.

[39] M.L. Gonçalves, L.D. Dimitrov, M.H. Jordão, M. Wallau, E.A. Urquieta-González, Synthesis of mesoporous ZSM-5 by crystallisation of aged gels in the presence of cetyltrimethylammonium cations, *Catalysis Today* 133–135 (2008) 69.

[40] H.J. Percival, J.F. Duncan, P.K. Foster, Interpretation of the Kaolinite-Mullite Reaction Sequence from Infrared Absorption Spectra, *J American Ceramic Society* 57 (1974) 57–61. <https://doi.org/10.1111/j.1151-2916.1974.tb10813.x>.

[41] H.J. Percival, J.F. Duncan, P.K. Foster, Interpretation of the Kaolinite-Mullite Reaction Sequence from Infrared Absorption Spectra, *J American Ceramic Society* 57 (1974) 57–61. <https://doi.org/10.1111/j.1151-2916.1974.tb10813.x>.

[42] S. Yang, P. Yuan, H. He, Z. Qin, Q. Zhou, J. Zhu, D. Liu, Effect of reaction temperature on grafting of γ -aminopropyl triethoxysilane (APTES) onto kaolinite, *Applied Clay Science* 62–63 (2012) 8–14. <https://doi.org/10.1016/j.clay.2012.04.006>.

[43] Department of Chemistry and Chemical Engineering, Hunan Institute of Science and Technology, Yueyang 414 006, Hunan, P.R. China, L.-J. He, S.-Q. Zheng, Department of Chemistry and Chemical Engineering, Hunan Institute of Science and Technology, Yueyang 414 006, Hunan, P.R. China, Y.-L. Dai, Yueyang Science and Technology Association, Yueyang 414 000, Hunan, P.R. China, An FCC Catalyst for Maximizing Gasoline Yield, *Kem. Ind.* 66 (2017) 9–15. <https://doi.org/10.15255/KUI.2016.028>.

[44] Z. Zhang, Z. Liu, R. Feng, P. Liu, Z. Yan, The development of FCC catalysts for producing FCC gasoline with high octane numbers, *Appl Petrochem Res* 4 (2014) 379–383. <https://doi.org/10.1007/s13203-014-0075-9>.

[45] A.M. Ribeiro, H.F. Machado Júnior, D.A. Costa, Kaolin and commercial fcc catalysts in

the cracking of loads of polypropylene under refinery conditions, *Braz. J. Chem. Eng.* 30 (2013) 825–834. <https://doi.org/10.1590/S0104-66322013000400014>.

[46] E.A. Emam, *Clays as Catalysts in Petroleum Refining Industry*, 3 (2013) 20.

[47] M. Enterría, F. Suárez-García, A. Martínez-Alonso, J.M.D. Tascón, Preparation of hierarchical micro-mesoporous aluminosilicate composites by simple Y zeolite/MCM-48 silica assembly, *Journal of Alloys and Compounds* 583 (2014) 60–69.

<https://doi.org/10.1016/j.jallcom.2013.08.137>.

[48] H. Jia, T. Du, X. Fang, H. Gong, Z. Qiu, Y. Li, Y. Wang, Synthesis of Template-Free ZSM-5 from Rice Husk Ash at Low Temperatures and Its CO₂ Adsorption Performance, *ACS Omega* 6 (2021) 3961–3972. <https://doi.org/10.1021/acsomega.0c05842>.

[49] A.S. Kovo, O. Hernandez, S.M. Holmes, Synthesis and characterization of zeolite Y and ZSM-5 from Nigerian Ahoko Kaolin using a novel, lower temperature, metakaolinization technique, *J. Mater. Chem.* 19 (2009) 6207.

<https://doi.org/10.1039/b907554b>.

[50] I.C.M. Costa, Adsorption/diffusion interplay in hierarchical zeolites : understanding the role of external surface and additional porosity, phdthesis, Université de Lyon, 2019.

[51] H. Youssef, D. Ibrahim, S. Komarneni, Microwave-assisted versus conventional synthesis of zeolite A from metakaolinite, *Microporous and Mesoporous Materials* 115 (2008) 527–534. <https://doi.org/10.1016/j.micromeso.2008.02.030>.

[52] I. Kabalan, Synthèse des matériaux nanoporeux pour la décontamination moléculaire et le stockage d'énergie, (n.d.).

[53] A.W. Chester, Dehydrocyclization of n-hexane by highly dispersed platinum in zeolite Y, *Journal of Catalysis* 86 (1984) 16–23. [https://doi.org/10.1016/0021-9517\(84\)90343-9](https://doi.org/10.1016/0021-9517(84)90343-9).

[54] J.-B. Pigot, Dynamique multi-échelle et échange inter-porosité par relaxométrie RMN au sein de zéolithes mésoporisées, (n.d.).

[55] K.P. de Jong, J. Zečević, H. Friedrich, P.E. de Jongh, M. Bulut, S. van Donk, R. Kenmogne, A. Finiels, V. Hulea, F. Fajula, Zeolite Y Crystals with Trimodal Porosity as Ideal Hydrocracking Catalysts, *Angew. Chem. Int. Ed.* 49 (2010) 10074–10078.

<https://doi.org/10.1002/anie.201004360>.

EXCLUDE CUSTOM MATCHES	ON
EXCLUDE QUOTES	OFF
EXCLUDE BIBLIOGRAPHY	OFF